

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 754 660 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
22.01.1997 Bulletin 1997/04

(51) Int. Cl.⁶: C04B 35/468, H01C 7/02,
H01B 3/12

(21) Application number: 96110759.6

(22) Date of filing: 03.07.1996

(84) Designated Contracting States:
DE FR GB

(30) Priority: 21.07.1995 JP 185754/95

(71) Applicant: TDK Corporation
Chuo-ku, Tokyo (JP)

(72) Inventors:
• Fukuda, Masaru
Kitakyushu-shi, Fukuoka (JP)

• Ogasawara, Tadashi
Chuo-ku, Tokyo (JP)
• Marui, Toshio
Chuo-ku, Tokyo (JP)


(74) Representative: Vogeser, Werner, Dipl.-Ing. et al
Patent- und Rechtsanwälte
Hansmann, Vogeser, Dr. Boecker,
Alber, Dr. Strych, Liedl
Albert-Rosshaupter-Strasse 65
81369 München (DE)

(54) Voltage-dependent nonlinear resistor ceramics

(57) A voltage-dependent nonlinear resistor or varistor ceramic composition consists essentially of (1) an oxide of the formula: $[(\text{Sr}_{1-x-y}\text{Ba}_x\text{Ca}_y)_2\text{TiO}_3]$ wherein $0.3 < x \leq 0.9$, $0.1 \leq y \leq 0.5$, $x + y \leq 1$, and $0.84 < z < 1.16$, (2) 0.001 to 5.000 mol% of at least one oxide of niobium, tantalum, tungsten, manganese or R wherein R is yttrium or lanthanide, (3) 0.001 to 5.000 mol% of

SiO_2 , and (4) 0.001 to 5.000 mol% of MgO. When the varistor voltage is controlled by changing a re-oxidizing temperature without changing the composition, a satisfactory nonlinear index α is available over a wide range of varistor voltage. The dependency of varistor voltage on heat treating temperature is reduced.

FIG. 3



EP 0 754 660 A1